



TITLE OF THE INVENTION

PERPENDICULAR MAGNETIC RECORDING MEDIUM AND MAGNETIC
RECORDING/REPRODUCTION APPARATUS

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application is based upon and claims the
benefit of priority from the prior Japanese Patent
Application No. 2002-216595, filed July 25, 2002,
the entire contents of which are incorporated herein
by reference.

10 BACKGROUND OF THE INVENTION

1. Field of the Invention

 The present invention relates to a magnetic
recording/reproduction apparatus used as a hard disk
apparatus and, more particularly, to a magnetic
15 recording/reproduction apparatus using perpendicular
magnetization and a perpendicular magnetic recording
medium for use in the apparatus.

2. Description of the Related Art

 An amorphous rare earth element-transition metal
20 alloy magnetic layer having perpendicular magnetic
anisotropy is generally used as a recording layer of
a magneto-optical recording medium.

 Recently, the use of this amorphous rare earth
element-transition metal alloy magnetic film as
25 a perpendicular magnetic recording layer of a
perpendicular magnetic recording medium such as a hard
disk is proposed in, e.g., Jpn. Pat. Appln. KOKAI

Publication Nos. 5-54358 and 2001-76332. However, the amorphous rare earth element-transition metal alloy magnetic layer is a continuous layer having no segregated structure, i.e., having neither magnetic
5 crystal grains nor grain boundaries. Therefore, if this layer is used as a magnetic recording medium, there is no core for keeping a written signal in a written place. As a consequence, a recorded signal shifts or disappears. This phenomenon often occurs
10 especially in high-frequency recording, so the amorphous rare earth element-transition metal alloy magnetic layer is unsuited to increasing the recording density of perpendicular magnetic recording.

Jpn. Pat. Appln. KOKAI Publication No. 2002-25031
15 discloses a perpendicular magnetic recording medium having a multilayered arrangement obtained by combining a material such as CoCr used in the conventional magnetic recording medium and the amorphous rare earth element-transition metal alloy magnetic layer.
20 Unfortunately, even this medium has the problem that the medium noise is larger than in the conventional recording medium using a CoCr recording layer.

As described above, a perpendicular magnetic recording layer using the conventional rare earth
25 element-transition metal alloy magnetic layer is unsuitable to increasing the recording density and is impractical because the medium noise is large.

BRIEF SUMMARY OF THE INVENTION

According to an embodiment of the present invention, there is provided a perpendicular magnetic recording medium characterized by comprising a
5 nonmagnetic substrate, a first perpendicular magnetic recording layer formed on the nonmagnetic substrate, having an easy axis of magnetization in the vertical direction to the surface of the medium, and mainly containing cobalt, and a second perpendicular magnetic
10 recording layer formed on the first perpendicular magnetic recording layer, having an easy axis of magnetization in the vertical direction to the surface of the medium, and mainly comprising a crystalline alloy which contains a rare earth element and a
15 transition metal.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

The accompanying drawings, which are incorporated in and constitute a part of the specification, illustrate presently embodiments of the invention and,
20 together with the generation description given above and the detailed description of the embodiments given below, serve to explain the principles of the invention.

FIG. 1 is a schematic sectional view showing
25 an example of a perpendicular magnetic recording medium of the present invention;

FIG. 2 is a schematic sectional view showing the

arrangement of another example of the perpendicular magnetic recording medium of the present invention;

FIG. 3 is a schematic sectional view showing the arrangement of still another example of the perpendicular magnetic recording medium of the present invention;

FIG. 4 is a schematic sectional view showing the arrangement of still another example of the perpendicular magnetic recording medium of the present invention;

FIG. 5 is a perspective view showing an example of a magnetic recording/reproduction apparatus of the present invention;

FIG. 6 is a schematic sectional view showing the arrangement of a perpendicular magnetic recording medium according to Example 1;

FIG. 7 is a schematic sectional view showing the arrangement of a conventional perpendicular magnetic recording medium;

FIG. 8 is schematic sectional view showing the arrangement of a perpendicular magnetic recording medium according to Comparative Example 2;

FIG. 9 is a graph showing the relationship between the cerium content and the SNR_m;

FIG. 10 is a graph showing the relationship between the gadolinium content and the SNR_m; and

FIG. 11 is a schematic sectional view showing the arrangement of a perpendicular magnetic recording medium according to Example 9.

DETAILED DESCRIPTION OF THE INVENTION

A perpendicular magnetic recording medium according to the first aspect of the present invention has an arrangement in which a first perpendicular magnetic recording layer having an easy axis of magnetization in the vertical direction to the surface of the medium, and a second perpendicular magnetic recording layer formed on the first perpendicular magnetic recording layer, having an easy axis of magnetization in the vertical direction to the surface of the medium are stacked in this order on a nonmagnetic substrate, in which the first perpendicular magnetic recording layer contains cobalt in a larger amount, the second perpendicular magnetic recording layer contains a crystalline alloy in a larger amount, and the crystalline alloy contains a rare earth element and a transition metal.

The first perpendicular magnetic recording layer mainly containing cobalt used in the present invention has a segregated structure having magnetic crystal grains and grain boundaries. On this recording layer, the second perpendicular magnetic recording layer mainly containing a crystalline alloy which contains a rare earth element and a transition metal is formed. According to the present invention, the size of the magnetic crystal grains growing from the first perpendicular magnetic recording layer is reduced,

and the grain boundaries is extended, thereby the segregated structure is further promoted. Also, since the magnetic recording layer has this double layered structure, its magnetic anisotropy can be further
5 increased compared to the conventional perpendicular magnetic recording medium having only one CoCr-based magnetic layer.

The present invention can achieve the following effects. First, the resolution of the perpendicular
10 magnetic recording layers, particularly, the second perpendicular magnetic recording layer can be increased by downsizing the magnetic crystal grains in the layer. Second, the thermal decay resistance can be increased by promoting the magnetic anisotropy of the whole
15 perpendicular magnetic recording layer. Third, the medium noise can be decreased by promoting the segregated structure of the perpendicular magnetic recording layers, particularly, the second magnetic recording layer.

20 If the content of the rare earth element is large in the alloy containing the rare earth element and the transition metal, the magnetic film often changes to an amorphous continuous film. Therefore, the present invention obtains a crystalline film by controlling,
25 e.g., the addition amount of the rare earth element and the thickness of the magnetic layer.

A soft magnetic layer can be formed as a backing

layer between the nonmagnetic substrate and first perpendicular magnetic recording layer.

This soft magnetic layer is made of a soft magnetic material having high magnetic permeability.

5 Examples are CoZrNb, FeTaC, FeZrN, FeSi alloy, FeAl alloy, FeNi alloy such as Permalloy, FeCo-based alloy such as Permendur, FeCoNi alloy such as Perminvar, NiCo alloy, sendust, MnZn-based ferrite, NiZn-based ferrite, MgZn-based ferrite, MgMn-based ferrite, FeAlGa,
10 FeCuNbSiB, FeGaGe, FeGeSi, FeNiPb, FeRuGaSi, FeSiB, FeSiC, FeZrB, FeZrBCu, CoFeSiB, CoTi, and CoZrTa.

When this high-magnetic-permeability soft magnetic layer is formed, a so-called double layered perpendicular recording medium having a perpendicular magnetic
15 recording layer on the soft magnetic layer is formed. In this double layered perpendicular recording medium, the soft magnetic layer performs part of the function of a magnetic head for magnetizing the perpendicular magnetic recording layer. That is, a recording
20 magnetic field supplied from the recording head to magnetize the perpendicular magnetic recording layer is moved in the horizontal direction and returned to the magnetic head by this soft magnetic layer. In this manner, the soft magnetic layer can increase the
25 recording/reproduction efficiency.

In addition, a ferromagnetic layer can be formed between the soft magnetic layer and nonmagnetic

substrate. After the medium is formed, a magnetic field is applied to this ferromagnetic layer in one radial direction, thereby applying a bias magnetic field to the soft magnetic layer and preventing the formation of magnetic domain walls.

Examples of the ferromagnetic layer are CoSm, CoPt, CoCrPt, and CoCrPtCu.

An undercoating such as Cr, V, or NiAl can also be formed between the soft magnetic layer and substrate.

On the obtained magnetic recording layer surface, a protective layer made of, e.g., carbon can be formed.

Furthermore, a lubricating layer can be formed by coating the perpendicular magnetic recording medium surface, e.g., the magnetic recording layer surface or protective layer surface, with a lubricating agent such as perfluoropolyether by dipping or the like.

FIG. 1 is a sectional view showing an example of the perpendicular magnetic recording medium of the present invention.

As shown in FIG. 1, a perpendicular magnetic recording layer 10 has an arrangement in which a soft magnetic backing layer 7, a first perpendicular magnetic recording layer 2 containing cobalt, and a second perpendicular magnetic recording layer 3 mainly containing a crystalline alloy which contains a rare earth element and a transition metal are stacked in this order on a nonmagnetic substrate 1 which is, e.g.,

a 2.5-inch glass substrate.

Examples of the transition metal used in the second perpendicular magnetic recording layer are cobalt and chromium.

5 Platinum can also be used as this transition metal.

 Examples of the rare earth element used in the second perpendicular magnetic recording layer are yttrium, lanthanum, cerium, praseodymium, neodymium,
10 samarium, europium, gadolinium, terbium, dysprosium, holmium, thulium, ytterbium, and lutetium.

 The rare earth element can contain in an amount of 0.1 to 20 at% in the second perpendicular magnetic recording layer. If the content is less than 0.1 at%,
15 the effect of reducing the size of the crystal grains by the addition of the rare earth element does not tend to appear. This tends to make the magnetic crystal grains and the noise larger than when 0.1 at% of the rare earth element is added. If the content exceeds
20 20 at%, the magnetic crystal grains tend to become an amorphous continuous film. Accordingly, the segregated structure of the second perpendicular magnetic recording layer tends to disappear, and the noise tends to increase.

25 The first perpendicular magnetic recording layer can contain at least one of platinum and chromium.

 In this case, the second perpendicular magnetic

recording layer can contain at least one element selected from the group consisting of yttrium, lanthanum, cerium, samarium, europium, thulium, ytterbium, and lutetium, and the content can be 0.1 to 20 at% in the second perpendicular magnetic recording layer. If the content is less than 0.1 at%, the effect by the addition of the rare earth element does not tend to appear. This makes the magnetic crystal grains and the noise larger than when 0.1 at% of the rare earth element is added. If the content exceeds 20 at%, the magnetic crystal grains tend to become an amorphous continuous film. Accordingly, the segregated structure of the second perpendicular magnetic recording layer tends to disappear, and the noise tends to increase.

Alternatively, the second perpendicular magnetic recording layer can contain at least one element selected from the group consisting of praseodymium, neodymium, gadolinium, terbium, dysprosium, and holmium, and the content can be 0.1 to 10 at% in the second perpendicular magnetic recording layer. If the content is less than 0.1 at%, the effect by the addition of the rare earth element does not tend to appear. This tends to make the magnetic crystal grains and the noise larger than when 0.1 at% of the rare earth element is added. If the content exceeds 10 at%, the magnetic crystal grains tend to become an amorphous continuous film. Accordingly, the segregated structure

of the second perpendicular magnetic recording layer tends to disappear, and the noise tends to increase.

The first perpendicular magnetic recording layer can further contain oxygen in addition to at least one
5 of platinum and chromium.

In this case, the rare earth element can be at least one element selected from the group consisting of yttrium, lanthanum, cerium, praseodymium, neodymium, samarium, europium, gadolinium, terbium, dysprosium,
10 holmium, thulium, ytterbium, and lutetium, and the content can be 0.1 to 20 at% in the second perpendicular magnetic recording layer. If the content is less than 0.1 at%, the effect by the addition of the rare earth element cannot be achieved. This makes the
15 magnetic crystal grains and the noise larger than when 0.1 at% of the rare earth element is added. If the content exceeds 20 at%, the magnetic crystal grains tend to become an amorphous continuous film. Accordingly, the segregated structure of the second
20 perpendicular magnetic recording layer tends to disappear, and the noise tends to increase.

At least one of Ta and Nb can be added to the alloy contained in the second perpendicular magnetic recording layer. By the addition of Ta and Nb, the
25 segregated structure further tends to advance to reduce the noise.

The addition amount of Ta and Nb can be 0.1 to

20 at% in the second perpendicular magnetic recording layer. If the addition amount is less than 0.1 at%, the effect by the addition of Ta and Nb does not tend to appear, and the noise reducing effect tends to be smaller than that of the medium to which these metals are added. If the addition amount exceeds 20 at%, excess Ta and Nb disturb the crystallinity, and the resolution significantly worsens.

The thickness of the second perpendicular magnetic recording layer can be 0.1 (inclusive) to 20 (exclusive) nm, and preferably, 0.1 (inclusive) to 15 (inclusive) nm. If the thickness is less than 0.1 nm, the effect of the second perpendicular magnetic recording layer does not appear. In this case, the magnetic crystal grains and the noise are larger than when the thickness is 0.1 nm or more. If the thickness is 20 nm or more, the crystallinity in the second perpendicular magnetic recording layer tends to deteriorate and to reduce the resolution.

As the material of the first perpendicular magnetic recording layer, it is possible to use, e.g., CoPt, CoCr, CoCrPt, CoCrO, CoPtO, CoPtCrO, CoCrPtB, CoCrPtTa, CoCrPtW, CoCrPtMo, CoCrPtCu, CoCrPtRu, CoCrPtWC, CoCrPtRuC, CoCrPtCuB, CoCrPtCuB, CoCrPtWB, CoCrPtTaCu, CoCrPtTaW, CoPt-SiO₂, and CoPtSiO.

The thickness of the first perpendicular magnetic recording layer can be 1 to 30 nm, and preferably, 5 to

20 nm. If the thickness is less than 1 nm, the segregated structure does not tend to well appear, so the noise tends to increase. If the thickness exceeds 30 nm, the size of the magnetic crystal grains tends to increase, and the resolution tends to worsen.

Two or more layers including the second perpendicular magnetic recording layer can be stacked on the first perpendicular magnetic recording layer.

FIG. 2 is a sectional view showing the arrangement of another example of the perpendicular magnetic recording medium of the present invention.

As shown in FIG. 2, a perpendicular magnetic recording medium 20 has the same arrangement as FIG. 1 except that a magnetic layer 4 made of, e.g., CoCrPtB is formed between first and second perpendicular magnetic recording layers 2 and 3.

Also, the first and second perpendicular magnetic recording layers can be alternately stacked on a nonmagnetic substrate.

FIG. 3 is a sectional view showing the arrangement of still another example of the perpendicular magnetic recording medium of the present invention.

As shown in FIG. 3, a perpendicular magnetic recording medium 30 has the same arrangement as FIG. 1 except that first and second perpendicular magnetic recording layers 2 and 3 are formed on other first and second perpendicular magnetic recording layers 2 and 3,

thereby alternately stacking the first and second perpendicular magnetic recording layers on a nonmagnetic substrate.

5 If two or more magnetic recording layers including the second perpendicular magnetic recording layer are stacked on the first perpendicular magnetic recording layer, the thickness of the whole magnetic recording layer can be 5 to 30 nm. If the thickness is less than 5 nm, the initial layer having inferior crystallinity
10 tends to occupy a large portion of the entire magnetic recording layer to worsen the resolution. If the thickness exceeds 30 nm, the size of the magnetic crystal grains tends to increase and the noise tends to increase.

15 An arbitrary interlayer can be formed between the first and second perpendicular magnetic recording layers and each magnetic layer. Examples of the interlayer are Cr, Mo, W, CrMo, CrW, CoCr, CoCrPt, and CoCrPtB. When this interlayer is formed, a segregation
20 source can be supplied from the interlayer, so the segregated structure can be promoted.

The thickness of this interlayer can be 0.1 to 5 nm. If the thickness is less than 0.1 nm, the segregated structure promoting effect by the interlayer
25 does not appear. If the thickness exceeds 5 nm, the crystallinity of the upper magnetic recording layer tends to disturb, and the resolution tends to worsen.

An arbitrary nonmagnetic undercoating or the like can be formed between the nonmagnetic substrate or the soft magnetic backing layer and the first perpendicular magnetic recording layer.

5 As this undercoating, it is possible to use, e.g., Ti, TiCr, Ru, RuCr, Hf, NiAl, NiTa, NiNb, CoCrPt, and CoCrPtB.

10 The thickness of the nonmagnetic undercoating used in the present invention can be 1 to 50 nm, and preferably, 5 to 30 nm. If the thickness is less than 1 nm, the crystallinity of the nonmagnetic undercoating tends to worsen. Accordingly, the crystallinity of the magnetic recording layer also tends to worsen, and the noise tends to increase. If the thickness exceeds
15 50 nm, the size of the magnetic crystal grains in the magnetic recording layer tends to increase, and the noise tends to increase.

20 FIG. 4 is a schematic sectional view showing the arrangement of still another example of the perpendicular magnetic recording medium of the present invention.

 As shown in FIG. 4, a perpendicular magnetic recording medium 40 has the same arrangement as FIG. 1 except that no soft magnetic backing layer 7 is formed.

25 An improvement of the resolution of this perpendicular magnetic recording medium can be not expected because this perpendicular magnetic recording medium is not a so-called double-layered perpendicular

medium that comprises a perpendicular magnetic recording layer on a soft magnetic backing layer. However, similar to the perpendicular magnetic recording medium according to the first aspect, it is possible to increase the resolution of the second perpendicular magnetic recording layer by reducing the size of the magnetic crystal grains in this layer, increase the thermal decay resistance by promoting the magnetic anisotropy of the whole perpendicular magnetic recording layer, and reduce the medium noise by promoting the segregated structure of the magnetic recording layers, particularly, the second magnetic recording layer.

A magnetic recording/reproduction apparatus according to the second aspect of the present invention comprises a perpendicular magnetic recording medium, a mechanism which supports and rotates the perpendicular magnetic recording medium, a magnetic head having an element to record information on the perpendicular magnetic recording medium and an element to reproduce recorded information, and a carriage assembly which supports the magnetic head to be movable with respect to the perpendicular magnetic recording medium, in which the perpendicular magnetic recording medium comprises a nonmagnetic substrate, a first perpendicular magnetic recording layer formed on the nonmagnetic substrate, having an easy axis of magnetization in the

vertical direction to the surface of the medium, and
a second perpendicular magnetic recording layer formed
on the first perpendicular magnetic recording layer,
having an easy axis of magnetization in the vertical
5 direction to the surface of the medium, the first
perpendicular magnetic recording layer mainly
containing cobalt, the second perpendicular magnetic
recording layer mainly comprising a crystalline alloy
which contains a rare earth element and a transition
10 metal.

FIG. 5 is a partially exploded perspective view
showing an example of the magnetic recording/
reproduction apparatus according to the present
invention.

15 A rigid magnetic disk 121 for recording
information according to the present invention is
fitted on a spindle 122 and rotated at a predetermined
rotational speed by a spindle motor (not shown).
A slider 123 mounting a single pole recording head for
20 accessing the magnetic disk 121 to record information
and an MR head for reproducing information is attached
to the end portion of a suspension 124 which is a thin
leaf spring. This suspension 124 is connected to one
end of an arm 125 having, e.g., a bobbin which holds
25 a driving coil (not shown).

A voice coil motor 126 as a kind of a linear
motor is attached to the other end of the arm 125.

This voice coil motor 126 includes the driving coil
(not shown) wound around the bobbin of the arm 125, and
a magnetic circuit having a permanent magnetic and
counter yoke opposing each other on the two sides of
5 the driving coil.

The arm 125 is held by ball bearings (not shown)
formed in two, upper and lower portions of a fixed
shaft 127, and pivoted by the voice coil motor 126.
That is, the position of the slider 123 on the magnetic
10 disk 121 is controlled by the voice coil motor 126.
Reference numeral 128 in FIG. 5 denotes a lid.

The present invention will be described in more
detail below by way of its examples.

Example 1

15 A nonmagnetic substrate made of a 2.5-inch
magnetic disk glass substrate was prepared.

This nonmagnetic substrate was placed in a vacuum
chamber having a vacuum degree of 1×10^{-5} Pa, the
substrate temperature was raised to 250°C, and DC
20 magnetron sputtering was performed in an Ar ambient at
a gas pressure of 0.6 Pa.

First, the nonmagnetic substrate was opposed to
a target, and discharge was performed on the target at
DC 500W, thereby forming a 40-nm thick Cr film as
25 a nonmagnetic undercoating for forming a ferromagnetic
layer. On top of this Cr film, a 25-nm thick CoCrPt
ferromagnetic layer was formed. On the obtained CoCrPt

ferromagnetic layer, a 200-nm thick CoZrNb soft magnetic backing layer was formed.

Subsequently, on the CoZrNb soft magnetic backing layer, a 5-nm thick Ti layer was formed as a first
5 undercoating by performing discharge on a Ti target at DC 300W. On the obtained Ti layer, a 20-nm thick nonmagnetic CoCrPt layer was formed by performing discharge on a Co-37at%Cr-8at%Pt target at DC 500W.

After that, a Co-20at%Cr-16at%Pt target was
10 prepared, and a 15-nm thick CoCrPt perpendicular magnetic recording layer was formed as a first perpendicular magnetic recording layer on the nonmagnetic CoCrPt undercoating.

A Co-20at%Cr-15at%Ce target was then used to form
15 a 9-nm thick CoCrCe perpendicular magnetic recording layer as a second perpendicular magnetic recording layer on the CoCrPt perpendicular magnetic recording layer.

Finally, a 7-nm thick carbon protective layer was
20 formed to obtain a perpendicular magnetic recording medium.

After the substrate thus continuously sputtered in the vacuum chamber was taken out into the atmosphere, a 1.5-nm thick perfluoropolyether (PFPE)-based
25 lubricating layer was formed by dipping, thereby obtaining a perpendicular magnetic recording medium.

FIG. 6 is a sectional view showing the arrangement

of the perpendicular magnetic recording medium according to Example 1.

As shown in FIG. 6, a perpendicular magnetic recording medium 50 has a structure in which a Cr nonmagnetic layer 5, CoCrPt ferromagnetic layer 6, CoZrNb soft magnetic film 7, Ti first undercoating 8, CoCrPt second undercoating 9, CoCrPt perpendicular magnetic recording layer 11, CoCrCe perpendicular magnetic recording layer 12, C protective layer 13, and lubricating layer (not shown) are stacked in this order on a nonmagnetic substrate 1.

The crystallinity of the CoCrCe perpendicular magnetic recording layer as the second perpendicular magnetic recording layer of the obtained perpendicular magnetic recording medium was checked as follows.

For comparison, a perpendicular magnetic recording medium was formed following the same procedure as in Example 1 except that no CoCrCe second perpendicular magnetic recording layer was formed.

FIG. 7 is a sectional view showing the arrangement of this perpendicular magnetic recording layer for comparison. As shown in FIG. 7, a perpendicular magnetic recording medium 60 has a structure in which a Cr nonmagnetic undercoating 5, CoCrPt ferromagnetic layer 6, CoZrNb soft magnetic layer 7, Ti first undercoating 8, CoCrPt second undercoating 9, CoCrPt perpendicular magnetic recording layer 11, C protective

layer 12, and lubricating layer (not shown) are stacked in this order on a nonmagnetic substrate 1.

5 X-ray diffraction measurement was performed for the obtained perpendicular magnetic recording media 50 and 60 to measure the Co (0002) peak intensity of the perpendicular magnetic recording layer. In the Co (0002) peak intensity of the perpendicular magnetic recording medium 40, overlapped signals from both Co in the CoCrPt first perpendicular magnetic recording layer and Co in the CoCrCe second perpendicular magnetic recording layer were observed. Therefore, X-ray diffraction measurement was performed for the perpendicular magnetic recording medium 50 to observe the Co (0002) peak intensity from the CoCrPt first perpendicular magnetic recording layer. The Co (0002) peak intensity of the CoCrCe second perpendicular magnetic recording layer was checked by calculating the Co (0002) peak intensity difference between these two perpendicular magnetic recording media. Consequently, 15 the Co (0002) peak intensity was clearly 100 cps or more, indicating that the CoCrCe second perpendicular magnetic recording layer was crystalline, not 20 amorphous.

25 A magnetic field of 15 kOe (about 1.2×10^6 A/m) was applied outward in the radial direction of the disk substrate of the perpendicular magnetic recording medium 40 by using a magnetizing apparatus having

an electromagnet, thereby magnetizing, in the radial direction, the CoCrPt ferromagnetic layer exhibiting longitudinal hard magnetism. The magnetoresistance effect of the magnetized perpendicular magnetic recording medium was used to evaluate the recording/reproduction characteristics by using a single pole head having a recording track width of $0.3\ \mu\text{m}$ and a reproduction track width of $0.2\ \mu\text{m}$. As a result, a differential waveform half width dPW50 as an index of the resolution was 89 nm, and SNR_m (S: low-frequency output, N: noise at 400 kFCI) was 23.9 dB, indicating that the medium was excellent. In addition, the decay value at a low-frequency output of 50 kFCI as a thermal decay index was -0.05%/decade. Table 1 shows the obtained results of dPW50 and SNR_m.

Comparative Example 1

A perpendicular magnetic recording medium was obtained following the same procedure as in Example 1 except that a 24-nm thick CoCrPt layer was formed as a first perpendicular magnetic recording layer on a nonmagnetic substrate similar to that of Example 1, and no CoCrCe layer as a second perpendicular magnetic recording layer was formed.

The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were evaluated in the same manner as in Example 1. The dPW50 as an index of the resolution was 105 nm,

and the SNRm was 17.1 dB. Also, the decay value at a low-frequency output of 50 kFCI was -0.15%/decade. Table 1 shows the obtained results of the dPW50 and SNRm.

5 Comparative Example 2

A perpendicular magnetic recording medium was obtained following the same procedure as in Example 1 except that on a nonmagnetic substrate similar to that of Example 1, a 9-nm thick CoCrCe layer as a second perpendicular magnetic recording layer was formed by using a Co-20at%Cr-15at%Ce target, and a 15-nm thick CoCrPt layer as a first perpendicular magnetic recording layer was formed by using a Co-20at%Cr-16at%Pt target.

15 FIG. 8 is a sectional view showing the arrangement of the perpendicular magnetic recording medium according to Comparative Example 2.

As shown in FIG. 8, a perpendicular magnetic recording medium 70 has a structure in which a Cr nonmagnetic layer 5, CoCrPt ferromagnetic layer 6, CoZrNb soft magnetic layer 7, Ti first undercoating 8, CoCrPt second undercoating 9, CoCrCe perpendicular magnetic recording layer 12, CoCrPt perpendicular magnetic recording layer 11, C protective layer 13, and lubricating layer (not shown) are stacked in this order on a nonmagnetic substrate 1.

The recording/reproduction characteristics of the

obtained perpendicular magnetic recording medium 70
were evaluated in the same manner as in Example 1.
As a consequence, the dPW50 was 115 nm, and the SNRm
was 15.2 dB. Also, the decay value at a low-frequency
5 output of 50 kFCI was -0.11%/decade. Table 1 below
shows the obtained results of the dPW50 and SNRm.

Table 1

	First magnetic layer	Second magnetic layer	SNRm (dB)	dPW50 (nm)
Example 1	CoCrPt	CoCrCe	23.9	89
Comparative Example 1	CoCrPt	CoCrPt	17.1	105
Comparative Example 2	CoCrCe	CoCrPt	15.2	115

Example 2

A plurality of different perpendicular magnetic
10 recording media having second perpendicular magnetic
recording layers different in thickness were formed
following the same procedure as in Example 1 except
that cerium was used and the film thickness of cerium
was properly changed from 0 to 30 nm.

15 Table 2 below shows the relationship between the
SNRm and the film thickness of the second magnetic
layer.

Table 2

Thickness of second magnetic layer	SNR _m (dB)
0	17.6
0.1	17.9
0.5	18.7
1	21.1
5	23.1
9	23.9
10	23.8
15	23.8
20	19.9
25	19.5
30	18.7

As shown in Table 2, the effect of increasing the SNR_m was obtained when the thickness of the second magnetic recording layer was 0.1 to 20 nm. The thickness of the second magnetic recording layer can be 1 to 15 nm.

Example 3

A perpendicular magnetic recording medium was obtained following the same procedure as in Example 1 except that a 9-nm thick CoCrPtCe layer was formed as a second perpendicular magnetic recording layer by using a Co-20at%Cr-14at%Pt-9at%Ce target.

The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were evaluated in the same manner as in Example 1. Consequently, dPW₅₀ = 85 nm and SNR_m = 24.2 dB, i.e., the medium had good characteristics. Also, the decay

value at a low-frequency output of 50 kFCI
was -0.06%/decade.

Example 4

5 A perpendicular magnetic recording medium was
obtained following the same procedure as for the
perpendicular magnetic recording medium 50 of Example 1
except that a 9-nm thick CoCrPtCeTa layer was formed as
a second perpendicular magnetic recording layer by
using a Co-20at%Cr-14at%Pt-9at%Ce-2at%Ta target.

10 The recording/reproduction characteristics of
the obtained perpendicular magnetic recording medium
were evaluated in the same manner as in Example 1.
Consequently, dPW50 = 83 nm and SNRm = 24.4 dB, i.e.,
the medium had good characteristics. Similar effects
15 were obtained by a perpendicular magnetic recording
medium using a 9-nm thick CoCrPtCeNb layer instead
of the CoCrPtCeTa layer. Also, the decay value at
a low-frequency output of 50 kFCI was -0.04%/decade.

Example 5

20 A plurality of perpendicular magnetic recording
media having Co-20at%Cr-Ce layers different in
composition ratio as second perpendicular magnetic
recording layers were formed following the same
procedure as in Example 1 except that cerium was used
25 as a rare earth element in the second perpendicular
magnetic recording layers, and the cerium composition
of a Co-20at%Cr-Ce target was properly changed from 0

to 25 at%.

The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were evaluated in the same manner as in Example 1. FIG. 9 is a graph showing the relationship between the cerium content and the SNRm as a result of the evaluation. This graph shown in FIG. 9 indicates that the SNRm was good when the cerium composition was 0.1 to 20 (exclusive) at%. Also, the Co (0002) intensity of the perpendicular magnetic recording layer of each of these perpendicular magnetic recording media was observed by X-ray diffraction measurement in the same manner as in Example 1. As a consequence, the Co (0002) intensity was clearly observed. Similar effects were obtained from perpendicular magnetic recording media using yttrium, lanthanum, thulium, ytterbium, and lutetium, instead of cerium.

Example 6

A plurality of perpendicular magnetic recording media having Co-20at%Cr-Gd layers different in composition were formed following the same procedure as in Example 5 except that gadolinium was used as a rare earth element, and the gadolinium composition of a Co-20at%Cr-Gd target was properly changed from 0 to 25 at%.

The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were

evaluated in the same manner as in Example 5. FIG. 10 is a graph showing the relationship between the gadolinium content and the SNRm as a result of the evaluation.

5 This graph shown in FIG. 10 indicates that the SNRm was good when the gadolinium composition was 0.1 to 10 (exclusive) at%. Also, the Co (0002) intensity of the perpendicular magnetic recording layer of each of these perpendicular magnetic recording media was
10 observed by X-ray diffraction measurement in the same manner as in Example 5. As a consequence, the Co (0002) intensity was clearly observed. Similar effects were obtained from perpendicular magnetic recording media using praseodymium, samarium, europium, terbium,
15 dysprosium, and holmium, instead of gadolinium.

Example 7

Following the same procedure as in Example 1, a CoCrPt ferromagnetic layer and CoZrNb soft magnetic backing layer were formed on a nonmagnetic substrate.

20 This substrate was cooled to decrease the substrate temperature to room temperature. Subsequently, on the CoZrNb soft magnetic backing layer, Ti was discharged at DC 300W to form a 4-nm thick Ti layer as a first undercoating. On this Ti
25 layer, Co-37at%Cr-8at%Pt was discharged as a second undercoating at DC 500W, thereby forming a 20-nm thick nonmagnetic CoCrPt layer.

After that, a Co-20at%Pt-16at%Cr target was used to form a 15-nm thick CoPtCrO perpendicular magnetic recording layer on the CoCrPt layer in an oxygen-containing argon ambient. Subsequently,
5 a Co-20at%Cr-15at%Ce target was used to form a 9-nm CoCrCe perpendicular magnetic recording layer.

Finally, a 7-nm thick C protective layer was formed on the CoCrCe perpendicular magnetic recording layer.

10 After the substrate on which the films were thus continuously formed in a vacuum chamber was taken out into the atmosphere, a 1.5-nm thick PFPE-based lubricating layer was formed by dipping, thereby obtaining a perpendicular magnetic recording medium.

15 The obtained perpendicular magnetic recording medium had the same arrangement as Example 1 except that the CoPtCrO perpendicular magnetic recording layer was formed instead of the CoCrPt perpendicular magnetic recording layer.

20 The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were evaluated in the same manner as in Example 1. As a consequence, SNR_m = 23.0 dB, indicating that the medium was excellent. Also, the dPW50 was 82 nm, and the
25 decay value at a low-frequency output of 50 kFCI was -0.07%/decade.

Similar effects were obtained from perpendicular

magnetic recording media using yttrium, lanthanum, praseodymium, neodymium, samarium, europium, gadolinium, terbium, dysprosium, holmium, thulium, ytterbium, and lutetium, instead of cerium.

5 Table 3 below shows the obtained results of the dPW50 and SNRm.

Table 3

Second magnetic layer	SNRm (dB)	dPW50 (nm)
CoCrY	22.5	90
CoCrLa	22.1	92
CoCrCe	23.0	93
CoCrPr	23.7	91
CoCrNd	22.6	92
CoCrSm	22.3	96
CoCrEu	22.6	94
CoCrGd	23.6	90
CoCrTb	21.1	85
CoCrDy	21.4	87
CoCrHo	20.9	89
CoCrTm	21.2	88
CoCrYb	20.4	84
CoCrLu	21.1	86
CoCrPt	16.8	111

10 Table 3 shows that the SNRm improves when light rare earth elements such as yttrium, lanthanum, cerium, praseodymium, neodymium, samarium, europium, and gadolinium are used as rare earth elements. On the other hand, the resolution dPW50 rather than the SNRm, improves when heavy rare earth elements such as terbium, dysprosium, holmium, thulium, ytterbium, and

lutetium are used as rare earth elements.

Comparative Example 3

5 A perpendicular magnetic recording medium was obtained following the same procedure as in Example 7 except that a CoCrPt layer was formed instead of the CoCrCe layer as a second perpendicular magnetic recording layer by using a Co-20at%Cr-16at%Pt target.

10 The recording/reproduction characteristics of the obtained conventional perpendicular magnetic recording medium were evaluated in the same manner as in Example 1. As a consequence, the SNR_m was 16.8 dB. Also, the dPW50 was 96 nm, and the decay value at a low-frequency output of 50 kFCI was -0.17%/decade.

Comparative Example 4

15 A perpendicular magnetic recording medium was obtained following the same procedure as in Example 7 except that a Co-20at%Pt-16at%Cr target was used to form a 24-nm thick CoPtCrO layer as a first perpendicular magnetic recording layer in an oxygen-containing argon ambient, and no CoCrCe layer was formed as
20 a second perpendicular magnetic recording layer.

The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were evaluated in the same manner as in Example 1. As a
25 consequence, the SNR_m was 17.3 dB. Also, the dPW50 was 98 nm, and the decay value at a low-frequency output of 50 kFCI was -0.12%/decade.

Example 8

A perpendicular magnetic recording medium was formed following the same procedure as in Example 1 except that discharge was performed at DC 300W on
5 a first perpendicular magnetic recording layer target made of Co-20at%Cr-16at% Pt and a second perpendicular magnetic recording layer made of Co-20at%Cr-15at%Ce, thereby alternately forming three 5-nm thick first perpendicular magnetic recording layers and three 5-nm
10 thick second perpendicular magnetic recording layers, i.e., forming a total of 30 nm of layers.

The recording/reproduction characteristics of the obtained perpendicular magnetic recording medium were evaluated in the same manner as in Example 1.
15 Consequently, $d_{PW50} = 80$ nm and $SNR_m = 22$ dB, i.e., the medium had good characteristics. Also, the decay value at a low-frequency output of 50 kFCI was $-0.04\%/decade$.

Example 9

A perpendicular magnetic recording medium was
20 formed following the same procedure as in Example 1 except that none of the nonmagnetic Cr undercoating 5, CoCrPt ferromagnetic backing layer 6, and CoZrNb soft magnetic backing layer 7 was formed. FIG. 11 shows the arrangement of this perpendicular magnetic recording
25 medium according to Example 9. As shown in FIG. 11, a perpendicular magnetic recording medium 70 has an arrangement in which a Ti first undercoating 8,

CoCrPt second undercoating 9, CoCrPt first
perpendicular magnetic recording layer 11, CoCrCe
second perpendicular magnetic recording layer 12, C
protective layer 13, and lubricating layer (not shown)
5 are stacked in this order on a nonmagnetic substrate 1.

Subsequently, the magnetoresistance effect was
used to evaluate the recording/reproduction character-
istics by using a ring head having a recording track
width of $0.3\ \mu\text{m}$ and a reproduction track width of
10 $0.2\ \mu\text{m}$. Consequently, the SNR_m was 20 dB, indicating
that the magnetic recording medium was excellent.
Also, the waveform half width PW50 as an index of the
resolution of a single layered perpendicular medium was
86 nm, and the decay value at a low-frequency output of
15 50 kFCI was $-0.07\%/decade$.

Comparative Example 5

A perpendicular magnetic recording medium was
obtained following the same procedure as in Example 9
except that a Co-20at%Cr-16at%Pt target was used
20 to form a 24-nm thick CoCrPt layer as a first
perpendicular magnetic recording layer on a nonmagnetic
substrate, and no CoCrCe second perpendicular magnetic
recording layer was formed.

The recording/reproduction characteristics of
25 the obtained conventional perpendicular magnetic
recording medium were evaluated in the same manner as
in Example 9. As a consequence, the SNR_m was 16.8 dB.

Also, the PW50 was 102 nm, and the decay value at a low-frequency output of 50 kFCI was -0.13%/decade.

Additional advantages and modifications will readily occur to those skilled in the art. Therefore,
5 the invention in its broader aspects is not limited to the specific details and representative embodiments shown and described herein. Accordingly, various modifications may be made without departing from the spirit and scope of the general inventive concept as
10 defined by the appended claims and their equivalents.